

Application No. 10/009,640

IN THE SPECIFICATION:

Replace the paragraph at page 40, lines 11-20 with the following revised paragraph:

--Subsequently, the hydrophilic polymer, CYMEL-701 functioning as a crosslinking agent and as a precursor of a hydrophobic polymer, and ~~Olester~~ OLESTER UD350 (aqueous dispersion urethane resin, available from Mitsui Chemicals, Inc., average particle diameter: about 30 nm) as a hydrophobic polymer in the amounts (solid content, part(s) by weight) shown in Table 3 were mixed with 1 part by weight of paratoluenesulfonic acid as a curing accelerator and 5 parts by weight of IR-125 as a light absorbing compound, to prepare a photosensitive composition.

Replace Table 3 at page 41 with the following revised Table

3:

Table 3

Example	7	8	9
Hydrophilic polymer (parts by weight)	60	50	35
CYMEL-701 (parts by weight)	30	30	35
<del>Olester</del> <u>OLESTER</u> UD350 (parts by weight)	10	20	30